

No-Tox[®] POLYOLEFIN INKS (PAD PRINT/SCREEN PRINT)

NT30
(12/14)

- Product Type:** Modified co-solvent polyamide polymers.
- Printing Method:** Either pad or screen printing depending on diluents and diluted viscosity.
- Suggested Uses:** Specifically designed for all types of polyolefin (polyethylene and polypropylene) films, molds, sheets or coated paperboard which will be in contact with food or pharmaceutical products. For optimum adhesion and abrasion resistance, items must be corona treated (40 dynes/cm² minimum) prior to printing.
- Specific Characteristics:** A one-part, air dry or heat-assisted curing system exhibiting excellent adhesion and abrasion resistance on corona treated polyolefins.
- Note:** Alcohol resistance of this system is poor. If alcohol resistance is required our NT24 system is recommended.
- Equipment Requirements:** *Pad Print:* compatible with all types of pad printing equipment and pads.
Screen Print: compatible with all types of screens and rubber squeegees.
Mesh size dependent on print and end-use requirements.
- Additives and Diluents*:** Both pad print and screen print versions of these inks are normally supplied at higher than “press-ready” viscosities to allow for viscosity and drying rate adjustment at press-side.
- Recommended Solvents:** The following solvents and blends are intended only as a guide. Other diluents and/or ratios may be better suited for your specific application. For additional assistance, contact our Technical Services Department.
- Normal: 50% Normal Butyl Alcohol
50% Benzyl Alcohol
- Fast: 100% Normal Propyl Alcohol.
- Slow: 100% Benzyl Alcohol
- Wash-Up:** The recommended diluents above may also be used for wash-up.
- Color Availability:** Black, red, blue, yellow and white are standard. Other shades can be prepared upon request.
- Shelf Life:** Minimum one year in unopened containers.
- Caution:** Storage at low temperatures (45°F or lower) may cause gelling. Gelling can usually be reversed by allowing the ink to come to room temperature and stirring with a high-shear mixer.
- FDA Acceptability*:** All components used in No-Tox Inks are sanctioned by the FDA and USDA as acceptable for direct food contact.

Note: FDA acceptability is based on the ink as supplied. Therefore no materials should be added other than those indicated in this bulletin unless specifically recommended by Colorcon



For more information, contact your Colorcon representative or call 1-800-724-0624
You can also visit our website at [http:// www.colorcon.com/notox](http://www.colorcon.com/notox)

©BPSI Holdings LLC, 2014

The information contained in this document is proprietary to Colorcon Inc. and may not be used or disseminated inappropriately.

All trademarks, except where noted, are property of BPSI Holdings, LLC.

The information contained herein, to the best of Colorcon Inc.'s knowledge, is true and accurate. Any recommendations or suggestions of Colorcon Inc. with regard to the products provided by Colorcon Inc. are made without warranty, either implied or expressed, because of the variations in methods, conditions and equipment which may be used in commercially processing the products, and no such warranties are made for the suitability of the products for any applications that you may have disclosed. Colorcon Inc. shall not be liable for loss of profit or for incidental, special or consequential loss or damages. The information contained in this document is not intended as legal advice, and should not be relied upon for that purpose. Any regulatory information provided is intended solely as initial general guidance. Each customer is responsible for determining the regulatory acceptability of the use of the product in their specific application.

