

Coating Parameters – Clear Formulations

CoreleaseCA™ is a dry blend of excipients for the application of a semipermeable membrane coating to osmotic pump tablets.

The coating parameters listed in the table below are based on Colorcon data for CoreleaseCA clear formulations. Individual product and machine functions should be taken into account and conditions altered as required.

		Fully Perforated Side Vented Coating Pan			
Pan Diameter	cm	33	44.5	38.1	61
	in	13	17.5	15	24
Solution Preparation					
Solvent		Acetone:water (94:6 - 90:10)	Acetone:water (94:6 - 90:10)	Acetone:water (94:6 - 90:10)	Acetone:water (94:6 - 90:10)
Solids Content	% w/w	7.0	7.0	7.0	7.0
Run Objectives					
Theoretical Weight Gain	% w/w	10	10	10	10
Tablet Charge†	kg†	1.0 - 2.0	4 - 5	2.5 – 3.5	13-15
Gun Configuration					
Example Spray Gun	type	Schlick	Schlick	Schlick	Schlick
Number of Guns	guns	1	1	1	2
Nozzle Diameter	mm	1.2	1.2	1.2	1.2
	in	0.05	0.05	0.05	0.05
Gun to Bed Distance	cm	6.5	6.5	6.5	8.9
	in	2.5	2.5	2.5	3.5
Gun to Gun Distance	cm	N/A	N/A	N/A	15
	in	N/A	N/A	N/A	6
Atomizing Air Pressure	bar	1.5	1.5	1.1 – 1.4	1.1 – 1.4
	psi	21	21	15 – 20	15 – 20
Pattern Air Pressure	bar	0.5	0.5	1.4	1.4
	psi	7.3	7.3	20	20
Process Parameters					
Drying Air Volume	cu.m/hr	136	136	272	425
	cu.ft/min	80	80	160	250
Pan Speed*	rpm*	18	15	18	14
Pre-warm Tablet Bed	°C	33 - 38	33 - 38	30 - 35	30 - 35
	°F	91 - 101	91 - 101	86 – 95	86 – 95
Inlet Air Temperature	°C	39 - 42	39 - 42	31 - 34	30 - 39
	°F	102 - 108	102 - 108	88 – 93	86 - 102
Tablet Bed Temperature	°C	26 - 29	26 - 29	26 - 29	24 – 28
	°F	79 - 84	79 - 84	79 - 84	75 - 82
Spray Rate	g/min	28 - 30	28 - 30	40 - 44	100 - 120
Approx. Coating Times	min	71 - 77	214 - 230	97 - 107	167 - 200
*Pan speed should be set so that even mixing of the bed occurs. This will be influenced by tablet size, shape, friability and baffle type in the pan.					
†Tablet charge is dependent on tablet size and shape.					

The information contained herein, to the best of Colorcon, Inc.'s knowledge is true and accurate. Any recommendations or suggestions of Colorcon, Inc. with regard to the products provided by Colorcon, Inc. are made without warranty, either implied or expressed, because of the variations in methods, conditions and equipment which may be used in commercially processing the products, and no such warranties are made for the suitability of the products for any applications that you may have disclosed. Colorcon, Inc. shall not be liable for loss of profit or for incidental, special or consequential loss or damages.

Colorcon, Inc. makes no warranty, either expressed or implied, that the use of the products provided by Colorcon, Inc., will not infringe any trademark, trade name, copyright, patent or other rights held by any third person or entity when used in the customer's application.

For more information, contact your Colorcon representative or call:

North America
+1-215-699-7733

Europe/Middle East/Africa
+44-(0)-1322-293000

Asia Pacific
+65-6438-0318

Latin America
+54-11-5556-7700

You can also visit our website at www.colorcon.com



© BPSI Holdings, 2010. The information contained in this document is proprietary to Colorcon, Inc. and may not be used or disseminated inappropriately.

All trademarks, except where noted, are property of BPSI Holdings,LLC.

pi_corelease_ca_param_clear_v1_11_2023